

SkimStone Coverage Chart

Quantities listed are for standard trowel applied, three-coat applications.

Sealer quantities listed will yield approximately 4 coats.

Colorant based on SkimStone of 4oz strength.



	Square Feet						
	100	200	400	600	800	1000	
Substrate 1							
Type I Solution (gallons)	0.21	0.42	0.84	1.27	1.69	2.11	
Powder (pounds)	1.39	2.78	5.56	8.34	11.12	13.90	
Sealer (gallons)	0.40	0.80	1.60	2.40	3.20	4.00	
Colorant (4oz jars)	0.21	0.42	0.84	1.27	1.69	2.11	
Substrate 2							
Type I Solution (gallons)	0.42	0.84	1.69	2.53	3.38	4.22	
Powder (pounds)	2.78	5.56	11.12	16.68	22.24	27.80	
Sealer (gallons)	0.40	0.80	1.60	2.40	3.20	4.00	
Colorant (4oz jars)	0.42	0.84	1.69	2.53	3.38	4.22	
Substrate 3							
Type I Solution (gallons)	0.84	1.69	3.38	5.06	6.75	8.44	
Powder (pounds)	7.40	14.80	29.60	44.40	59.20	74.00	
Sealer (gallons)	0.40	0.80	1.60	2.40	3.20	4.00	
Colorant (4oz jars)	0.84	1.69	3.38	5.06	6.75	8.44	
Substrate 4							
Type I Solution (gallons)	Starting with the ratio for a #3 rank, slowly add additional powder until a thick but workable mixture is achieved. This applies ONLY to the first coat. All subsequent coats are mixed for a #1 rank substrate.						
Powder (pounds)							
Sealer (gallons)							
Colorant (4oz jars)							
Substrate 5							
Type I Solution (gallons)	Starting with the ratio for a #3 rank, slowly add additional powder until a thick but workable mixture is achieved. This applies ONLY to the first coat. All subsequent coats are mixed for a #1 rank substrate.						
Powder (pounds)							
Sealer (gallons)							
Colorant (4oz jars)							

Substrate Definitions

- 1 - Surface appears glossy and is smooth in appearance and to the touch. Few or no cracks present.
- 2 - Surface dull and smooth in appearance. Texture resembles fine sandpaper. Few or no cracks present.
- 3 - Surface dull and rough in appearance. Texture resembles very coarse sandpaper. Some exposed aggregate and cracks present.
- 4 - Surface very rough in appearance. Surface quite weathered and aggregate exposed.
- 5 - Surface extremely rough or "broomed". Surface weathered and aggregate exposed with deep recesses present throughout.

Caution: A surface is rarely a #1 rank substrate. This coverage chart assumes ideal application conditions for humidity, temperature, and substrate absorbance. Coverage numbers are calculated exactly to the square foot for the substrate rank and no additional material is assumed.